
DURACELL®

CR123A

Lithium/Manganese Dioxide Battery





Dimensions shown are IEC/ANSI standards

Key Features

- Industry Highest Cell Capacity & High Energy
- High voltage response, stable during most of the lifetime of the application
- Reliable Performance
- Wide operating temperature range (- 20°C / + 75°C)
- Low self-discharge with long operating life (<1% after 1 year of storage at + 20 °C)
- Excellent resistance to corrosion
- Designed to meet all major quality, safety and environment standards:
 - o Safety: IEC 60086-4
 - o Transport: UN 38.3
 - o RoHS and REACH compliance
 - o Quality: ISO 9001, Duracell World Class Continuous Program

Electrical characteristics

•	Nominal capacity (100 Ohm Cont., 2V cut-off)	1550 mAh
٠	Typical Voltage (at + 20 °C)	3.2-3.3 V
•	Standard Continuous Discharge Current	20 mA
•	Maximum Continuous Discharge Current	60 mA
•	Maximum Abnormal Charge Current	25 mA
•	Nominal Energy	4.35 Wh
•	AC Impedance @ 1kHz	350 mOhm

Physical characteristics

•	Typical weight	17.0 g (0.60 oz.

Li metal content approx. 0.53g

Operating & Storage conditions

•	Operating temperature range	-20°C to 75°C
		(-4°F to 167°F)

Recommended Storage (storage area should 5°C to 30°C be clean, cool, dry and ventilated (41°F to 86°F)



Delivered capacity is dependent on the applied load, operating temperature and cut-off voltage. Please refer to the charts and discharge data shown for examples of the energy/service life that the battery will provide for various load conditions.


DURACELL®


CR123A


Lithium/Manganese Dioxide Battery


Typical applications


- Cameras
- Security devices (sensors, monitoring cameras)
- Smoke Detectors
- Wireless Sensors
- Door locks
- Pet Training Collars
- High Intensity Flashlights
- Laser Sights













Delivered capacity is dependent on the applied load, operating temperature and cut-off voltage. Please refer to the charts and discharge data shown for examples of the energy/service life that the battery will provide for various load conditions.

Results filtered on a load value of 0.56 W


DURACELL®

CR123A

Lithium/Manganese Dioxide Battery

60086-4 © IEC:2007 Edition 3.0

Test	Test designation	Observation
А	Altitude	Pass
В	Thermal cycling	Pass
С	Vibration	Pass
D	Shock	Pass
Е	External short circuit	Pass
F	Impact	Pass
G	Crush	Pass
Н	Forced discharge	Pass
I	Abnormal charging	Pass
J	Free fall	Pass
K	Thermal Abuse	Pass



Service Hours

Warning

Fire, explosion and burn hazard Do not recharge, short circuit, crush, disassemble, heat above 100 $^{\circ}$ C (212 $^{\circ}$ F), incinerate, or expose contents to water



Delivered capacity is dependent on the applied load, operating temperature and cut-off voltage. Please refer to the charts and discharge data shown for examples of the energy/service life that the battery will provide for various load conditions.