-20°C to 75°C


(-4°F to 167°F)



## CR2

## Lithium/Manganese Dioxide Battery





#### **Key Features**

- Industry Highest Cell Capacity & High Energy
- High voltage response, stable during most of the lifetime of the application
- Reliable Performance
- Wide operating temperature range (- 20°C / + 75°C)
- Low self-discharge with long operating life (<1% after 1 year of storage at + 20 °C)
- Excellent resistance to corrosion
- Designed to meet all major quality, safety and environment standards:

o Safety: IEC 60086-4 o Transport: UN 38.3

o RoHS and REACH compliance

Quality: ISO 9001, Duracell World Class Continuous Program

#### **Electrical characteristics**

•	Nominal capacity (100 Ohm Cont., 2V cut-off)	920 mAh
•	Typical Voltage (at + 20 °C)	3.2-3.3 V
•	Standard Continuous Discharge Current	20 mA
•	Maximum Continuous Discharge Current	60 mA
•	Maximum Abnormal Charge Current	20 mA
•	Nominal Energy	2.55 Wh
•	AC Impedance @ 1kHz	500 mOhm

### **Physical characteristics**

•	Typical weight	11 g (0.39 oz.)
	Li metal content	approx. 0.30g

### **Operating & Storage conditions**

Operating temperature range

Recommended Storage (storage area should	
• • •	5°C to 30°C
be clean, cool, dry and ventilated	(41°F to 86° F)



Delivered capacity is dependent on the applied load, operating temperature and cut-off voltage. Please refer to the charts and discharge data shown for examples of the energy/service life that the battery will provide for various load conditions.

# **DURACELL**®


## CR2


## Lithium/Manganese Dioxide Battery


## **Typical applications**


- Cameras
- Security devices (sensors)
- **Smoke Detectors**
- Wireless Sensors
- Remote Controls
- Pet Training Collars
- High Intensity Flashlights
- Laser Sights













Delivered capacity is dependent on the applied load, operating temperature and cut-off voltage. Please refer to the charts and discharge data shown for examples of the energy/service life that the battery will provide for various load conditions.

# **DURACELL®**

# CR2

## Lithium/Manganese Dioxide Battery

#### 60086-4 © IEC:2007 Edition 3.0

Test	Test designation	Observation
А	Altitude	Pass
В	Thermal cycling	Pass
С	Vibration	Pass
D	Shock	Pass
Е	External short circuit	Pass
F	Impact	Pass
G	Crush	Pass
Н	Forced discharge	Pass
I	Abnormal charging	Pass
J	Free fall	Pass
K	Thermal Abuse	Pass

### Warning

Fire, explosion and burn hazard Do not recharge, short circuit, crush, disassemble, heat above 100 °C (212 °F), incinerate, or expose contents to water



Delivered capacity is dependent on the applied load, operating temperature and cut-off voltage. Please refer to the charts and discharge data shown for examples of the energy/service life that the battery will provide for various load conditions.