


# LITHIUM-MANGANESE DIOXIDE BATTERY



**Size: DURPC123**



**Dimensions shown are IEC standards**

## KEY FEATURES

- High voltage response, stable during most of the lifetime of the application
- Reliable Performance
- Low self-discharge with long operating life (<1% after 1 year of storage at + 20 °C)
- Excellent resistance to corrosion
- Designed to meet all major quality, safety and environment standards:
- Safety: IEC 60086-4
- Transport: UN 38.3
- RoHS and REACH compliance
- Quality: ISO 9001, Duracell World Class Continuous Program

## ELECTRICAL CHARACTERISTICS

▪ Nominal capacity (100 Ω Cont., 2V cut-off)	1550 mAh
▪ Typical Voltage (at + 20 °C)	3.2-3.3 V
▪ Standard Continuous Discharge Current	20 mA
▪ Maximum Continuous Discharge Current	60 mA
▪ Maximum Abnormal Charge Current	25 mA
▪ Nominal Energy	4.35 Wh
▪ AC Impedance @ 1kHz	350 mΩ

## PHYSICAL CHARACTERISTICS

▪ Typical weight	17.0 g (0.60 oz.)
▪ Li metal content	approx. 0.53g

## OPERATING & STORAGE CONDITIONS

▪ Operating temperature range	-20°C to 75°C (-4°F to 167°F)
▪ Recommended Storage (storage area should be clean, cool, dry and ventilated)	5°C to 30°C (41°F to 86°F)

Delivered capacity is dependent on the applied load, operating temperature and cut-off voltage. Please refer to the charts and discharge data shown for examples of the energy/service life that the battery will provide for various load conditions.


This data is subject to change. Performance information is typical. Contact Hamer for the latest information.



130 Bush Road  
Albany, 0632  
Telephone: 0800 239 239  
[www.hamer.co.nz](http://www.hamer.co.nz)

### TYPICAL APPLICATIONS

- Cameras
- Security devices (sensors, monitoring cameras)
- Smoke Detectors
- Wireless Sensors
- Door locks
- High Intensity Flashlights
- Laser Sights



### WARNING

- Fire, explosion and burn hazard
- Do not recharge, short circuit, crush, disassemble, heat above 100 °C (212 °F), incinerate, or expose contents to water

60086-4 © IEC:2007 EDITION 3.0

Test	Test designation	Observation
A	Altitude	Pass
B	Thermal cycling	Pass
C	Vibration	Pass
D	Shock	Pass
E	External short circuit	Pass
F	Impact	Pass
G	Crush	Pass
H	Forced discharge	Pass
I	Abnormal charging	Pass
J	Free fall	Pass
K	Thermal Abuse	Pass



130 Bush Road  
 Albany, 0632  
 Telephone: 0800 239 239  
[www.hamer.co.nz](http://www.hamer.co.nz)

Delivered capacity is dependent on the applied load, operating temperature and cut-off voltage. Please refer to the charts and discharge data shown for examples of the energy/service life that the battery will provide for various load conditions.

This data is subject to change. Performance information is typical. Contact Hamer for the latest information.